



Gesteinkörnung : 0/2 Edelbrechsand UNG
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil
Werte auf die sich der produzent verpflichtet
Norme

Lieferkörnung

0	2
---	---

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

a

	0.063	0.08	0.125	0.25	0.5	D/2 1	D 2	1.4D 2.8	2D 4	SE	W	f
Ausmas	6					20	10					
V.S.S.+U	17.0					72	98					
V.S.S.	16.0					71	96					16.00
V.S.I.	10.0					51	86	98	100	60.00		
V.S.I.-U	9.0					50	84	97	100			

Informative Teil
Production resultat

von 09/03/15 bis 29/07/15

	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	SE	W	f
Maxi	14.3	16.6	23	33	49	71	96	100	100	69.53	2.2	14.31
Xk+1.25xAbstand-type	14.3	16.5	22	33	49	72	97	100	100		2.3	14.33
Mittelwert Xf	12.7	14.4	20	30	44	64	93	100	100	64.88	1.8	12.71
Xk-1.25xAbstand-type	11.1	12.4	18	27	38	56	89	100	100		1.3	11.09
Mini	10.2	11.1	15	24	34	54	86	99	100	60.45	0.8	10.18
Abstand-type	1.29	1.62	1.9	2.6	4.3	6.1	3.2	0.2	0.0	3.220	0.40	1.295

