

Producteur : SAS Ballastières Werny
Produit : Granulats:Péetrographie=ASC,0/14 mm

Utilisateur : Contrôle Interne

Résultats de production

du 21/01/08 au 12/11/08

	0.063	0.5	1	2	4	6.3	8	10	14	20	W	f
CI-GNT/8/04	5.00	16.22	23.60	36.27	56.08	70.15	77.70	86.61	98.16	100.00	7.2	5.00
CI-GNT/8/08	0.13	9.13	15.17	25.50	41.62	54.46	63.67	74.85	96.27	100.00	7.1	0.13
CI-GNT/8/11	3.86	12.27	18.34	28.82	44.50	55.51	63.25	75.26	96.80	100.00	7.0	3.86
CI-GNT/8/15	3.86	12.54	18.70	29.31	45.62	59.03	65.49	75.98	97.40	100.00	7.5	3.86
CI-GNT/8/26	4.90	14.42	20.34	30.27	46.09	58.58	66.81	78.09	97.43	100.00	6.4	4.90
CI-GNT/8/27	5.72	17.18	25.01	37.76	59.30	73.87	80.15	84.46	95.35	100.00	5.8	5.72
CI-GNT/8/33	4.98	16.26	23.15	36.89	58.20	71.60	75.97	80.76	95.91	100.00	6.3	4.98
CI-GNT/8/38	4.68	13.86	20.38	31.54	52.34	70.46	74.75	79.15	93.60	100.00	6.2	4.68
CI-GNT/8/43	5.01	17.43	24.90	36.47	53.72	68.15	75.06	83.64	95.61	100.00	9.5	5.01
CI-GNT/8/46	5.02	14.94	21.33	34.00	53.63	70.61	74.83	80.32	91.63	100.00	4.3	5.02
Maximum	5.72	17.43	25.01	37.76	59.30	73.87	80.15	86.61	98.16	100.00	9.5	5.72
Xf+1.25xEcart-types	6.18	17.49	24.84	37.65	58.46	74.06	79.21	84.70	98.14	100.00	8.3	6.18
Moyenne Xf	4.32	14.42	21.09	32.68	51.11	65.24	71.77	79.91	95.82	100.00	6.7	4.32
Xf-1.25xEcart-types	2.45	11.36	17.34	27.72	43.76	56.43	64.33	75.12	93.49	100.00	5.1	2.45
Minimum	0.13	9.13	15.17	25.50	41.62	54.46	63.25	74.85	91.63	100.00	4.3	0.13
Ecart-type	1.494	2.451	2.997	3.970	5.881	7.053	5.954	3.834	1.857	0.000	1.30	1.494
Nombre de résultats	10	10	10	10	10	10	10	10	10	10	10	10

