



Gesteinkörnung : 0/2 Edelbrechsand UNG
Petrographischer Typ : Alpine Moräne - Oberrheinkies und sand

Normative Teil

Werte auf die sich der produzent verpflichtet

Norme

Lieferkörnung

0	2
---	---

Norme XP P 18-545 Article 8 - EN 13043

Kategorie

a

	0.063	0.08	0.125	0.25	0.5	D/2 1	D 2	1.4D 2.8	2D 4	f	SE	W
Ausmas	6					20	10					
V.S.S.+U	17.0					72	98					
V.S.S.	16.0					71	96			16.00		
V.S.I.	10.0					51	86	98	100		60.00	
V.S.I.-U	9.0					50	84	97	100			

Informative Teil

Production resultat

von 21/10/24 bis 10/02/25

	0.063	0.08	0.125	0.25	0.5	1	2	2.8	4	f	SE	W
Maxi	13.9	16	20	31	46	67	95	100	100	13.92		22.8
Xk+1.25xAbstand-type	14.0	16	21	31	46	67	96	100	100	14.02		11.2
Mittelwert Xf	12.8	15	19	28	42	63	93	100	100	12.76		4.5
Xk-1.25xAbstand-type	11.5	13	17	25	38	59	91	100	100	11.50		0.0
Mini	10.1	12	15	22	33	54	89	100	100	10.06		1.5
Abstand-type	1.01	1.1	1.5	2.3	3.2	3.3	1.8	0.1	0.0	1.006		5.30

