



Granulats : 16/22.4 roulé
Péetrographie : Alluvionaie silico-calcaire

Partie contractuelle
Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire			Norme											Catégorie				
16	22.4	Norme XP P 18-545 Article 10 - EN 12620 et EN 13139											Code A					
		d/2					d				D			1.4D	2D			
	0.063	8	10	12.5	14	16	18	20	22.4	25	31.5	45	f	FI	W			
Etendue e						15			15									
V.S.S.+U	2.1	6				25			100					24.00				
V.S.S.	1.5	5				20			96				1.50	20.00				
V.S.I.		0				5			81		98	100						
V.S.I.-U		0				0			76		97							

Partie informative
Résultats de production

du 19/02/24 au 27/01/25															
	0.063	8	10	12.5	14	16	18	20	22.4	25	31.5	45	f	FI	W
Maximum	0.0	0	1	3	9	20	45	70	89	99	100	100	0.05	18.56	1.7
Xf+1.25xEcart-types	0.0	0	1	3	7	19	43	67	87	99	100	100	0.04		1.7
Moyenne Xf	0.0	0	0	2	4	14	35	58	84	97	100	100	0.02	13.50	1.4
Xf-1.25xEcart-types	0.0	0	0	0	2	10	28	50	80	95	100	100	0.00		1.1
Minimum	0.0	0	0	1	2	8	25	47	81	94	100	100	0.00	0.00	1.1
Ecart-type	0.01	0.1	0.2	0.9	2.2	3.7	6.1	6.8	2.8	1.6	0.0	0.0	0.014	6.199	0.20

