



Granulats : 4/16R
Péetrographie : Alluvionaie silico-calcaire

Partie contractuelle
Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire		Norme												Catégorie		
4 16		Norme XP P 18-545 Article 10 - EN 12620 et EN 13139												Code A		
		d/2	d	D/2				D				1.4D	2D	f	FI	W
		0.063	2	4	5	5.6	6.3	8	10	12.5	16	20	22.4	31.5		
Etendue e								35								
V.S.S.+U		2.1	6	20				66			100				24.00	
V.S.S.		1.5	5	15				60			99				1.50	20.00
V.S.I.				0				25			90		98	100		
V.S.I.-U				0				19			85		97			

Partie informative
Résultats de production

du 21/10/24 au 10/02/25																
	0.063	2	4	5	5.6	6.3	8	10	12.5	16	20	22.4	31.5	f	FI	W
Maximum	0.1	0	13	27	36	45	62	75	90	99	100	100	100	0.08	17.47	4.7
Xf+1.25xEcart-types	0.0	0	10	22	30	39	58	74	89	99	100	100	100	0.04		4.1
Moyenne Xf	0.0	0	7	17	23	31	48	65	82	98	100	100	100	0.01	15.59	3.2
Xf-1.25xEcart-types	0.0	0	4	11	16	23	38	55	75	97	100	100	100	0.00		2.3
Minimum	0.0	0	4	12	17	24	39	57	75	96	100	100	100	0.00	13.44	1.7
Ecart-type	0.02	0.0	2.3	4.6	5.6	6.7	8.0	7.6	5.5	0.9	0.0	0.0	0.0	0.021	1.659	0.70

